




CLIMASEF AG 60 μ



Description & Application :

This 7-layer film is crystal clear and is specially designed to be used in low tunnels and as an early seed-bed cover.

KEY FEATURES	Specifications	Units	Nominal values	According to
	Thickness (average)	μm	$\pm 5\%$	NF EN 13206
	Thickness (at any point)	μm	$\pm 15\%$	NF EN 13206
	Width	-	$\pm 2\%$	ISO 4592
	Color	-	Crystal Clear	-
	Elongation at break (MD)	%	≥ 400	ISO 527-3
	Tensile stress at break (MD)	MPa	≥ 30	ISO 527-3
	Elongation at break (TD)	%	≥ 400	ISO 527-3
	Tensile stress at break (TD)	MPa	≥ 30	ISO 527-3
	Dart drop test on full film <i>Made on whole perimeter right after the production</i>	gr	≥ 150	ISO 7765-1
	Thermicity	%	Non thermal	EN 13206
	Global light transmission	%	> 92	EN 2155-5
	Haze	%	≤ 15	EN 2155-9

This information is provided for reference purposes only and is not intended as a warranty or guarantee. This information is subject to change without prior notice. Please contact AGRIPOLYANE for updated information. AGRIPOLYANE assumes no liability in connection with the use of this information.

Regarding our experience, the antidrip effect lasts 18-24 months. Because of the complex nature of these antidrip additives, we do not provide any guarantees. We assume no responsibility for non functioning of this property.

Contact



ZI Clos Marquet - BP 188 - 42408 SAINT CHAMOND CEDEX - FRANCE
Tél. : +33 (0)4 77 31 10 00
www.agripolyane.com

Réf: CLIMASEF AG 60 μ 2026.01.21 GB